

Technical Data Sheet

Tuffbond[®] 322

April 2019

Page 1 of 1

Product Description

Hernon[®] Tuffbond[®] 322 is a transparent 1:1 flexible, low viscosity, general purpose resin system used for casting, potting, and encapsulating of electrical and electronic components. This unique product has been formulated to combine ease in handling with optimum physical, thermal and electrical insulation properties.

Typical Applications

- Potting electronic boards
- Potting battery components
- Encapsulating electrical and electronic components
- Transformers
- Coils and chokes
- Solenoids
- Micro circuitry

Product Benefits

- Low viscosity
- Low shrinkage
- Room temperature or heat curing
- Can be used on metals, PVC, phenolics

Typical Properties (Uncured)

Property	Part A	Part B
Base	Epoxy	Modified Amine
Appearance	Clear Pale Yellow	Pale Yellow
Viscosity at 25°C, cP	10,000 to 16,000	12,000 to 18,000
Specific Gravity	1.16	1.15
Mix Ratio, by Volume	1	1

Typical Properties (Cured)

Physical Properties

Property	Value
Working Life at 22°C (30g), hours	3– 4 hours
Durometer Hardness, Shore A	25 - 45

Typical Cured Performance

Shear Strength

Steel lap-shear specimens tested according to ASTM D1002.

Conditioning	Shear Strength (psi)
G/B Steel, Cured 24 hours at RT	300 - 1000

General Information

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

1. For best results, make sure parts are clean and dry.
2. Dispense the product through a static mixer or mix the product (A&B) until thoroughly blended.
3. Apply completely mixed adhesive to the prepared surfaces.

Storage

Tuffbond[®] 322 should be stored in a cool, dry location in unopened containers at a temperature between 68°F to 86°F (20°C to 30°C) unless otherwise labeled. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon[®] Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.