

ROYCO® 22MS

HIGH LOAD CAPACITY, WIDE TEMPERATURE RANGE
SYNTHETIC BASED GREASE

Description

ROYCO 22MS is a smooth, gray - black colored synthetic oil based grease compounded with micro fine graphite and molybdenum disulfide for enhanced extreme pressure load carrying performance. **ROYCO 22MS** is compounded with additives to provide corrosion resistance, oxidation stability, rust protection, and water washout resistance over extreme temperature ranges.

Applications

ROYCO 22MS is recommended for use in heavily-loaded sliding steel surfaces and applications where severe operating conditions may include temperatures as high as 450 °F and as low as -65 °F. low speeds, high loads, extreme pressures on sliding surfaces, splines, ball screws, and anti-friction bearings where the graphite and MOS₂ may provide an added measure of protection against seizure in the event of inadequate lubrication due to extreme temperatures or mechanical spread out of the lubricant.

Features and Benefits

Features	Benefits
High viscosity index synthetic hydrocarbon (PAO) base stock	Very wide operating temperature range - outstanding high and low temperature performance Excellent film protection at high temperatures Minimum resistance to start-up at extremely low temperatures
Extreme-pressure additives, including high quality molybdenum disulfide	Protects sliding steel surfaces even under heavily-loaded conditions. Minimizes excessive wear, even under shock loading
High thermal/oxidative stability	Extended intervals between re-lubrication
High resistance to water washout	Maintains excellent grease performance in adverse weather or other water-exposure related conditions

Specifications

ROYCO 22MS meets all requirements of and is qualified under **MIL-G-81827A Notice 1**.

PROPERTY	METHOD	TYPICAL
Penetration, 25°C, 0.1 mm		
Unworked	ASTM D217	276
Worked		282
Worked Stability	FTM 313	320
Dropping Point, °C	ASTM D2265	292 (517)
4-Ball Wear, 75°C, 40 kg, 1200 rpm, 1 hr, mm	ASTM D2266	0.5
Oil Separation, 177°C (350°F), 30 hrs, %	FTM 321	1.4
Boiling Water Immersion	FTM 3463	Pass
Rust Protection, 125°F, 48 hours	ASTM D1743	Pass
Evaporation, 177°C, 22 hrs, Al Block, wt% loss	ASTM D2595	5.7
Load Carrying Capacity, kgf	ASTM D2596	35
Copper Corrosion at 100°C, 24 hrs, ASTM	ASTM D4048	Pass
Water Resistance, 41°C, %		1B
Low Temperature Torque, -54°C, Nm		
Starting Torque	ASTM D1478	0.5
Running Torque, 60 minutes		0.08
Odor		pass

Limitations

ROYCO 22MS should not be used on surfaces other than steel-on- steel without prior performance evaluation.

Packaging

ROYCO 22MS is available in 35-pound pails and 400 pound drums. Other package sizes may be available on request.

The information contained herein relates to a specific Chemtura product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet constitutes a term or condition of sale nor shall it take precedence over, supersede or modify or be construed to take precedence over, supersede or modify, any of Chemtura's standard or other terms and conditions of sale under which the product is sold by Chemtura. NOTHING IN THIS TECHNICAL DATA SHEET CONSTITUTES, NOR SHALL IT BE CONSTRUED TO CONSTITUTE, A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner. This product is sold only under terms and conditions agreed in writing by Chemtura and the respective buyer and the terms and conditions of such agreements shall in all cases prevail. ANDEROL, ROYCO, AOSyn and PQ and their corresponding logos are trademarks of Chemtura Corporation or one of its subsidiaries. Copyright (c) 2010 Chemtura Corporation. All rights reserved.



Anderol Specialty Lubricants
a division of Chemtura Corporation
215 Merry Lane
East Hanover, New Jersey 07936
Technical Service +1.973.887.7410
Customer Service +1.203.573.4595
Fax +1.203.573.2324
info-anderol@chemtura.com
www.anderol.com