


Premium Self-Wound Foil Tape



Backing: Aluminum Foil
Adhesive: Acrylic
Liner: N/A
Colors: Aluminum
Specifications: Meets FAR 25.853(a), SAE AMS-T-23397B (supercedes MIL-T-23397A & B) & L-T-80B
 Tested in accordance with UL 723

Applications

- Speed Tape
- Window mask to protect aircraft canopies, windshields, and passenger window surfaces from crazing or hazing during paint stripping operations
- Masking tape in paint stripping and electroplating applications
- Condenser and evaporator fastener in the appliance and refrigeration industry
- Aircraft sealing and masking
- Heavy duty vapor barrier sealing for sheet metal flexible, and fiberglass duct systems
- Insulation seal, patch, and repair
- Composite repair and manufacturing
- Heat shielding and elimination of "hot" spots in industrial maintenance applications
- Diversion trough for wash-off of paints and chemicals during stripping and painting process

Features

- Heavy-Duty Dead Soft Aluminum Foil Backing
- Acrylic Adhesive
- Self Wound Construction

Benefits

- Smooth, easy unwind
- Provides a barrier to air, moisture and corrosion
- Acts as a heat shield to minimize heat transfer
- Conformable for irregular surfaces and contours
- Excellent bond to most surfaces
- Solvent resistant
- Excellent high temperature performance
- Permits clean, easy removal with no residue
- No release liner minimizes waste

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	5.0 mils	0.127 mm	PSTC-133
Foil Thickness	3.0 mils	0.076 mm	PSTC-133
Adhesion to Steel	68 oz/in	7.44 N/cm	PSTC-101
Tensile Strength	26 lb/in	45.53 N/cm	PSTC-131
Elongation	3%		PSTC-131
Operating Temperature	-40 to 350 °F	-40 to 177 °C	

Recommended Storage Conditions: 60-80 °F at 40-60% RH
 Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.