

# EC75 Epoxy Topcoat

## TECHNICAL DATA SHEET

### Product Description

EC75 is a two pack, epoxy topcoat designed to provide protection of internal structures of aircraft and land based equipment.

- Excellent adhesion properties
- Applicable over epoxy & polyurethane primers
- Available in a wide range of gloss levels
- High chemical resistance
- High resistance to aircraft fluids including phosphate ester hydraulic fluid

### Components



#### Mix Ratio

BASE	ACTIVATOR	THINNER	MIX RATIO (by volume)	FINISH
EC75	ACT65	T17	1: 1: 0.5-1.0	Full Gloss
EC75	ACT66	T17	1: 1: 0.5-1.0	Semi Gloss
EC75	ACT67	T17	1: 1: 0.5-1.0	Eggshell
EC75	ACT68	T17	1: 1: 0.5-1.0	Matt
EC75	ACT69	N/A	2:1	Full Gloss (Brushing)

### Specifications



EC75 is qualified to:

- DEF STAN 80-161
- MSRR9064

#### Product Compatibility

EC75 is compatible with the following primer / filler specifications:

- BS2X32
- BS2X33A+B
- Def Stan 80-206
- Def Stan 80-207
- Def Stan 80-216

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

# EC75 Epoxy Topcoat

## Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended overcoat window for primers.

## Instructions for Use



Hand stir or mechanically shake base material until all components are uniformly dispersed. Add to base appropriate activator for gloss level required. Stir thoroughly and add thinner (if required).

*Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**

Not required




### **Viscosity:** ( 23°C/73°F)

• AFNOR2.5	58 - 67 seconds
• AFNOR4	16 - 18 seconds
• BSB3	30 - 35 seconds
• BSB4	18 - 21 seconds
• FORD4	15 - 17 seconds
• ISO3	55 - 70 seconds
• ISO4	24 - 33 seconds
• ZAHN2	20 - 22 seconds

No viscosity check required for brush application

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

8 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature	15 - 35°C (59 - 95°F)
Relative Humidity	30 - 85 %

# EC75 Epoxy Topcoat

## Application:

Apply one double track coat to achieve recommended dry film thickness of  $30 \pm 5\mu\text{m}$ .




## Theoretical Coverage: (ready for use with ACT65)

11 m<sup>2</sup>/Lt @ 30  $\mu\text{m}$  dry film thickness  
440 ft<sup>2</sup>/US gal @ 1.2 mil dry film thickness

## Recommended Dry Film Thickness:

25 - 35  $\mu\text{m}$   
1 - 1.4 mil



## Dry Film Density: (mixed with ACT65)

1.13 - 1.64 g/cm<sup>3</sup>  
9.45 - 13.7 lbs/US gal

## Dry Film Weight:

34 - 49 g/m<sup>2</sup> @ 30  $\mu\text{m}$  dry film thickness  
0.006 - 0.010 lbs/ft<sup>2</sup> @ 1.2 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Equipment:** EC75 is compatible with most current types of spray equipment.



Equipment Type	Tip Size	Pressure
Conventional Spray	1.2 to 1.5mm	44 to 73 psi (3 to 5 bar)

EC75 can be applied by brush. (See mix ratio table)

## Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

# EC75 Epoxy Topcoat

## Physical Properties



### Colour:

Wide range of colours available




### Gloss:

- Full Gloss: >85 units with a 60° gloss meter
- Semi-Gloss: 50-60 units with a 60° gloss meter
- Eggshell: 15-25 units with a 60° gloss meter
- Matt: ≤ 5 units with a 60° gloss meter



Drying Times 50 % R.H.	23°C (73°F)	70°C (158°F)
Dust Free	90 minutes	
Hard Dry	16 hours	30 minutes
Dry to Overcoat	4 to 72 hours	
Dry to Fly	48 hours	3 hours
Full Cure	7 days	3 hours

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



### Flash Off:

15 minutes after application prior to force dry.



### VOC: (ASTM)

Mixed unthinned (spraying)	<590 g/Lt
Mixed ready for use (brushing)	<510 g/Lt
EC75 Base	<530 g/Lt
ACT65 Activator	650 g/Lt
ACT66 Activator	610 g/Lt
ACT67 Activator	600 g/Lt
ACT68 Activator	565 g/Lt
ACT69 Activator	460 g/Lt
T17 Thinner	830 g/Lt

## EC75 Epoxy Topcoat

**Flash Point:**

EC75 Base	20°C (68°F)
ACT65 Activator	20°C (68°F)
ACT66 Activator	20°C (68°F)
ACT67 Activator	20°C (68°F)
ACT68 Activator	20°C (68°F)
ACT69 Activator	23°C (73°F)
T17 Thinner	16°C (61°F)


**Shelf Life:**

EC75 Base Component	24 months in original unopened container
ACT65 Activator	24 months in original unopened container
ACT66 Activator	24 months in original unopened container
ACT67 Activator	24 months in original unopened container
ACT68 Activator	24 months in original unopened container
ACT69 Activator	24 months in original unopened container
T17 Thinner	10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

### **Storage Recommendations**



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*



# EC75 Epoxy Topcoat

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC - South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP  
[www.ppgaerospace.com](http://www.ppgaerospace.com)  
Issue Date: 10/14  
Lit: 4220