

DeSoto® 823-707 Integral Fuel Tank Coating


TECHNICAL DATA SHEET

Product Description

DeSoto® 823-707 Integral Fuel Tank Coating is used to protect the interior of an aircraft's fuel tank against corrosion from fuel contaminants. 823-707 is a chemically-cured coating which provides maximum protection against water, salt water, aircraft fuels, hydraulic fluids, engine oils, and dilute acid solutions.

- Excellent adhesion to aluminum
- Compatible with fuel tank sealants
- Exceptional fluid resistance
- Superior durability
- Compatible with all current non-electrostatic spray equipment
- Service temperature -54°C to 177°C (-65°F to 350°F)

Components



Mix ratio (by volume):

- | | |
|---------------------------------|---------|
| • 823-707 (base component) | 4 parts |
| • 910-702 (activator component) | 1 part |
| • 020-707 (thinner component) | 4 parts |

Specifications



823-707 coating is qualified to:

- | | |
|---|---------------------|
| • AMS-C-27725 Type II | • GAMPS 3102 Type 2 |
| • BMS 10-101 Class B | • GC 130AS |
| • DHMS C4.06 Type I | • MS-194 |
| • DMS 1850 Types 1, 3, & 4
Composition A | • STO 125 LB 006 |

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

DeSoto[®] 823-707 Integral Fuel Tank Coating

Product Compatibility:

823-707 is compatible with the following sealant specifications:

- 207-6-466
- ACS-MRS-7006
- AMS 3265
- AMS 3276
- AMS 3277
- AMS 3281
- AMS-S-8802
- HMS 16-1097
- FMS 1044
- FMS 3064
- DMS 2082
- GMS 4115
- MS-402
- MMS332

Surface Preparation and Pretreatments



DeSoto[®] 823-707 Integral Fuel Tank coatings can be applied over clean dry, intact aluminum surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-C-5541 or equivalent

Instructions for Use



Mixing Instructions:

Prior to mixing, thoroughly shake the base component. Add activator to base component and stir well, and add the thinner while stirring. Maintain constant agitation for 10 minutes to ensure proper mixing. Induction time may be required.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13°C to 35°C (55°F to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.



Induction Time:

Temperature	13-21°C (55-70°F)	22-28°C (71-84°F)	>29°C (>85°F)
Induction Time Required	45 minutes	30 minutes	15 minutes


DeSoto[®] 823-707 Integral Fuel Tank Coating



Viscosity: (23°C/73°F)

- | | |
|-------------------------|------------------|
| • #2 Signature Zahn cup | 15 to 26 seconds |
| • #4 Ford cup | 10 to 20 seconds |
| • ISO 4mm cup | 17 to 40 seconds |
| • BSB3 cup | 24 to 42 seconds |
| • BSB4 cup | 14 to 24 seconds |
| • AFNOR #2.5 cup | 41 to 87 seconds |
| • AFNOR #4 cup | 14 to 22 seconds |

Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.



Pot Life:

8 hours @ 21-25°C (70-77°F)

Application Guidelines

Recommended Application conditions:

Temperature	15-30°C (59-86°F)
Relative Humidity	10-90%

Application:


Ground the aircraft and the application equipment before priming. Stir the coating slowly during the application. The suggested film thickness is 20 to 30 microns (0.8 to 1.2 mils). This can be accomplished with one medium coat with a 50% overlap.

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

9.79 square meters/liter at 25 microns dry film (399 square feet/gallon at 1 mil dry film)
 Recommended dry film thickness; 20 to 30 microns (0.8 to 1.2 mils)



Dry Film Density:

1.74 grams/cubic centimeter (14.5 pounds/gallon)

Dry Film Weight:

43.5 grams/square meter at 25 microns dry film (0.00891 pounds/square feet at 1 mil dry film)



DeSoto[®] 823-707 Integral Fuel Tank Coating



Equipment:

823-707 coatings are compatible with all forms of non-electrostatic spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto[®] CN20, DeSoto[®] CN44, or Desoclean[™] 45 high performance solvent cleaner.

Physical Properties (product)



Color: Yellow



Gloss: Not Applicable



Dry Times at 10-90% R.H.	13-21°C (55-70°F)	22-28°C (71-84°F)	>29°C (>85°F)
Tack Free	3 hours	2 hours	1 hour
Dry Hard	36 hours	24 hours	18 hours
Full Cure	14 days	14 days	14 days

Accelerated cure at minimum 10-50% R.H. at 60°C (140°F):

Dry hard

Flash off for 2 hours, then force cure for 3-4 hours

Full cure

Flash off for 2 hours, then force cure for 24-36 hours

DeSoto[®] 823-707 Integral Fuel Tank Coating



VOC:

Mixed, ready for use VOC (EPA method 24)	650 grams/liter
Base Component	491 grams/liter
Activator Component	118 grams/liter
Thinner Component	832 grams/liter



Flash point closed cup:

Base Component	-6°C (22°F)
Activator Component	-6°C (22°F)
Thinner Component	-1°C (31°F)

Shelf Life:

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

DeSoto[®] 823-707 Integral Fuel Tank Coating

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200

Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119

Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666

Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International,
Inc.

12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 4/17
Lit: 4196