

# ALPHA<sup>®</sup> 615 Series Super RMA Flux

## DESCRIPTION

**ALPHA 615** flux meets MIL-F-14256 requirements for flux type RMA, making it suitable for all Military work requiring conformance to DOD-STD-2000. **ALPHA 615** also meets the IPC-J-004 standard for type ROL0, the lowest flux residue corrosivity category and the highest surface insulation resistance rating.

The standard solids content for **ALPHA 615** is 37%. Where use of a lower solids flux is appropriate, such as when wave soldering surface mount boards, **ALPHA 615-25** (25% solids) and **ALPHA 615-15** (15% solids) are available.

## FEATURES & BENEFITS

- Maximum achievable RMA activity. Very fast wetting flux.
- Very cleanable, even with high preheat. No white residue.
- Excellent foaming properties. Uniform, consistent flux coverage.

## ACTIVITY

**ALPHA 615** is the most effective soldering flux yet developed for achieving excellent soldering yields with complex Military assemblies, while clearly passing all requirements for an RMA, non-conductive, non-corrosive flux.

Wetting balance and solder spread tests are widely used quantitative measures for comparing flux activity. The faster the speed of solder wetting, as measured by the wetting balance, and the greater the area of solder spread, i.e. spread factor percent, the more efficient the flux is for promoting solder wetting. The superior activity of 615 can be seen from the following test data:

	<b>Alpha 615</b>	<b>Kester 185</b>	<b>Almit RF35M</b>
Spread Factor <sup>1</sup>	91.7%	90.2%	86.8%
Wetting Speed <sup>2</sup>	0.41 seconds	0.47 seconds	0.64 seconds

<sup>1</sup> Test conducted using oxidized copper and 60Sn/40Pb flowed at 500°F for 15 seconds.

<sup>2</sup> Test conducted using oxidized copper, 60Sn/40Pb at 500°F, 5 mm immersion depth and 10 sec cycle time.

Wetting speed measured as time for wetting to reach equilibrium.

**ALPHA 615** has also demonstrated the ability to prevent solder icicle formation, when tested according to the method developed by Philips-Eindhoven, Netherlands, "Determination of the Flux Efficiency to Prevent Formation of Icicles (and Bridges)."

# ALPHA<sup>®</sup> 615 Series Super RMA Flux

## SAFETY

**ALPHA 615** is flammable. Keep away from heat, sparks and open flames. Observe standard precautions for handling and use, such as in well-ventilated areas and avoidance of prolonged or repeated contact with skin. Consult the SDS for all safety information. The most recent version of the SDS is available from AlphaAssembly.com.

## PACKAGING

**ALPHA 615** series fluxes are available in 1, 5 and 55 gallon containers.

## USE

**ALPHA 615** is designed for wave soldering printed circuit assemblies that must use an RMA flux meeting military specifications. While formulated to have excellent foaming properties, wave and spray fluxing can also be used.

All three solids levels of 615 flux should be maintained by periodic measurement of flux specific gravity (corrected to 77°F) and kept to within +0.015 and -0.005 of the nominal values.

While topside preheat temperatures of 180-200°F are sufficient for 615 flux activation, higher preheat conditions may be required for assemblies that have significant heat sinking characteristics, or when attempting to minimize the temperature gradient that ceramic chip components see between preheat and the solder wave.

Under conditions of extreme preheat, most RMA fluxes become extremely difficult to clean after soldering, especially with mild fluorocarbon-blend solvents. **ALPHA 615** flux residues clean very well with either mild fluorocarbon-blend solvents or aqueous saponifier (**ALPHA 2110**).

## TECHNICAL DATA

Physical Properties	Typical Values		
	615	615-25	615-15
Appearance		Clear, amber liquid	
Specific Gravity @ 77°F ± .005	0.878	0.845	0.818
Solids Content, % wt/wt	37	25	15
Water Extract Resistivity, ohm-cm, per MIL-F-14256, typical	170,000	190,000	225,000
Shelf Life (from Date of Manufacturing)	540 days	540 days	540 days

# ALPHA® 615 Series Super RMA Flux

Chlorides and Bromides, per MIL-F-14256 (Silver Chromate Paper)	Pass	Pass	Pass
Copper Mirror, per MIL-F-14256	Pass	Pass	Pass
Copper Corrosion, IPC-J-STD-004	No Corrosion	No Corrosion	No Corrosion
Surface Insulation Resistance:			
35°C/90% RH, comb-down, uncleaned, per Bellcore GR-78, CORE Issue 1		> 1.0 x 10 <sup>11</sup> ohms	
85°C/85% RH, comb-down, uncleaned, per IPC-SF-818, Class 3		>1.0 x 10 <sup>9</sup> ohms	
Flash Point (T.C.C.)		53°F	
Recommended Alpha Thinner		438	

## CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions

AlphaAssembly.com

<p><b>North America</b> 300 Atrium Drive Somerset, NJ 08873, USA 800.367.5460</p>	<p><b>Europe</b> Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400</p>	<p><b>Asia</b> 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	---	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions.™ Trademark of MacDermid Performance Solutions.  
© Platform Specialty Products Corporation and its subsidiaries 2016.