# Cor-Ban®

CORROSION INHIBITING COMPOUNDS

## D-5026NS



Product description: AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>

### FEATURES:

A medium to heavy duty water displacing, thin film, corrosion preventive compound

#### **KEY BENEFITS:**

- Contains no ozone depleting chemicals
- Prevents corrosion and displaces water
- Provides superior protection to avionic connectors and components and has lubricating properties to prevent fretting corrosion
- Protects electrical connectors from corroding
- Protects cables, surfaces, and interior and exterior aircraft surfaces



- D-5026NS contains a thixotropic property to prevent it from disrupting contact between connectors
- Corrosion protection provides protection in the harshest environments
- Coating can withstand temperatures up to 105°C (221°F) for only 500 hours cumulative
- Contains a film that prevents oxidation of the substrate

Rev: 20065J 11-30-2021





# **Cor-Ban**<sup>®</sup>

#### **CORROSION INHIBITING COMPOUNDS**

## D-5026NS



Product description: AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>

### **KEY BENEFITS:**

 Useful for initial protection during shipment and storage and for inservice treatment of critical areas

## SPECS:

- Boeing Alert Service Bulletin 737-24A1148 (Called out as CIC for connectors), AD 2002-16-03 (Called out)
- DPM-5707-1 (QPD)
- Embraer E6125209 (QPD)
- Sikorsky SS 8536 Type 1 (QPD)

### **APPLICATIONS:**

- $\checkmark\,$  Use on highly critical metal surfaces and avionic components
- ✓ D-5026NS can be used in conjunction with the Formit<sup>®</sup> extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the Formit<sup>®</sup> technical data sheet for more information.
- ✓ Store at 40°F-100°F (4°C-38°C)
- ✓ Bulk application available as ZC-026
- ✓ One aerosol covers approximately 140 ft<sup>2</sup> (13m<sup>2</sup>)
- ✓ For removal of D-5026NS, use D-5640NS, Sur-Prep<sup>®</sup> 3160, or Sur-Prep<sup>®</sup> 3167

For more information contact us : zipchem@addevmaterials.com

- The cured film can withstand temperatures as low as -55°C (-67°F) and as high as 85°C (185°F) continuously
- MIL-PRF-81309H Type II & III, Class 2, Grade CO2 (QPD)
- NSN: 8030-01-603-2129 (16 fl oz (473 ml) Aerosol) (QPD)
- NSN: 8030-01-603-2131 Type II (16 fl oz (473 ml) Aerosol) (QPD)





# Cor-Ban®

#### **CORROSION INHIBITING COMPOUNDS**

## D-5026NS



Product description: AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>

## **PHYSICAL PROPERTIES:**

- **Evaporation Rate:** Faster than ether
- Flame Extension: Flammable
- Fungal Growth per Fed-STD-810 Method 508.7: 0 (No Microbial Growth)
- Outgassing per ASTM E-595
  - Total Mass Loss (TML): 49%
  - Collected Volatile Condensable Material (CVCM): 27.3%
- Shelf Life: 3 years from date of shipment
- Specific Gravity (H<sub>2</sub>O=1): 0.86
- Vapor Density: Heavier than air

## AVAILABLE PACK SIZES:

- Case of 12 of 16 fl oz (473 ml) Aerosols-007669
- Case of 4 each Gallon (4 each of 3.8 L) Cans-009415
- ▶ 5 Gallon (18.9 L) Pail-002095
- 55 Gallon (208 L) Drum-002076
- Special Packaging Upon Request

For more information contact us : **zipchem@addevmaterials.com** 

