

DAPCO™ 2200

Dapco™ 2200 is an adhesive, two-component, solvent-free, thixotropic silicone paste. Dapco™ 2200 is most commonly used as a coating, sealant, or filleting material in the construction, repair and maintenance of all types of aircraft. The product can be applied using a variety of methods and is especially useful where fire resistance, exposure to phosphate ester fluids, and/or exposure to extreme temperatures -65°F (-54°C) to 400°F (204°C) are major considerations. The product can also be used as an insulative and/or ablative heat shield. The product is available in kit sizes of 2.5 oz and 6 oz injection kits.

Features and Benefits

- Quick Cure
- Excellent fire resistance to 2000°F (1093°C)
- Service temperature of -65°F (-54°C) up to 400°F (204°C)
- Universal primerless adhesion to diverse substrates
- Good resistance to aerospace chemicals
- Offers non-inhibition curing characteristics against other sealants and adhesives
- Non-Volatile Content of >96%
- Qualified to BMS 5-63, BAMS 552-004, and AMS3374

CHARACTERISTICS

Table 1 | Physical Properties

Property	Part A	Part B	Mixed
Solids, %	100	100	100
Consistency	Paste	Viscous Liquid	Thixotropic Paste
Density, lb/gal (kg/L)	11.6 (1.39)	7.8 (0.94)	11.4 (1.37)
Shore Hardness ASTM D 2240	Shore A: 50		
Shelf Life ¹	6 months stored at or below 75°F (24°C)		

¹ Keep in unopened foil bags.

Table 2 | Product Availability

Property		
Color	Part A Part B Mixed	Gray White Gray
Kit Size	2.5 oz 6.0 oz	

Table 3 | Flammability Properties of Dapco™ 2200

Property	DAPCO 2200	Substrate
Flame Resistance BMS 5-63	Self-extinguishing Time: < 2 sec	0.050 in (1.27 mm) Titanium, TI-6AL-4V
	Flame Penetration: None	

PROPERTIES

When cured in accordance with the recommended schedule, the following typical properties are developed:

Table 4 | Mechanical Properties of Dapco™ 2200

Property	DAPCO 2200	Substrate	
Lap Shear Strength ASTM D 1002	psi (MPa)	0.050 in (1.27 mm) Included: Stainless Steel, Titanium, Aluminum (bare), and Aluminum (bare) primed	
	Control		330 (2.3)
	7 days at 400°F (204°C)		330 (2.3)
	7 days at 120°F (49°C) & 100% RH 7 days in Skydrol® LD4 Hydraulic Fluid		260 (1.8)
Floating Roller Peel ASTM D 3167	lb/in(kN/m)	0.025 in (0.63 mm) and 0.064 in (1.63 mm) Aluminum	
	20 (3.5)		

PROCESSING

HANDLING

Mixing

Part A and B must be mixed in the correct ratio and mixed thoroughly. Product is supplied in injection kits and comes with mixing instructions. Mechanical mixing is recommended.

Parts	Weight
Part A	100
Part B	4.4

Tack Free Time

60 minutes

Work life

Product will extrude from the tube adequately for 30 minutes after mixing.

APPLICATION

Applying

The substrate must be free from contamination, i.e. dirt, oil grease, etc. Clean the surface by wiping with a suitable solvent/cleaning agent and dry thoroughly. Handling strength is achieved in less than 4 hours at 75°F (24°C) (loads on the product should be limited until full cure is achieved).

Curing

Dapco™ 2200 is generally cured at ambient temperatures above 55°F (13°C). Moisture helps develop final properties (a relative humidity ranging between 30% - 70% is preferred). Product reaches a hardness of 30 shore A in 4 hours at 75°F (24°C) and 50% R.H., allowing for quick repairs and fast “fly away” times. Full cure is achieved in 48 hours, however optimum physical properties are developed when the product is cured for a minimum of seven days for sealing applications and 14 days for faying surface applications at 75°F (24°C) and 50% R.H.

TECHNICAL DATA SHEET
DAPCO™ 2200
FIREWALL SEALANT

Cure may be inhibited by proximity or contact with a variety of materials including old RTV silicone sealant of the tin-cure variety, polysulfide, sulfur, amine and amide compounds, natural, nitrile or other organic rubbers, paper masking tape, plasticizers, lubricants, release agents or solvents.

Cleanup

Before the material has cured, the excess may be removed using commercial solvent. For optimum removal of silicone residue prior to paint or coating application, Dapco™ 2000 diluent is recommended.

HEALTH & SAFETY

Please refer to the product SDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2016, Solvay. All rights reserved.

Solvay

Composite Materials HQ
4500 McGinnis Ferry Rd
Alpharetta, GA 30005-3914 USA

TDS DAPCO™ 2200_2018_01_10

