



Issued : 01/2001

PR 1773 Class A

CORROSION INHIBITIVE SEALANT NON - CHROMATE LOW ADHESION

USE

PR 1773 Class A2 is a non-chromate corrosion inhibitive sealant designed for use as access door sealant.

It can also be used to protect electrical wires, terminal and equipment against fuel, moisture, dirt and short circuits.

DESCRIPTION

PR 1773 Class A2 is a two-part manganese cured, polysulfide-based sealant characterized by low adhesion properties.

The mixed compound is of fluid consistency which can be readily applied by brush, once applied around fasteners will not drip or flow from vertical or overhead surfaces.

SPECIFICATION

The following tests are in accordance with:

AMS 3267 specification test method.
Qualified to ASNA 4168 /A-A2.

PURCHASING

PRODUCT DESIGNATION

When ordering this product, designate PR number, class letter, and dash number as follows :

PR 1773 A-2 (application life : 2 h.)

STANDARD PACKAGING

DESIGNATION

KITS :

	Base Volume	Container	Number of Kits per case
KIT n° 10	0,10 liter	1/4 l. Can	12
KIT n° 25	0,25 liter	1/2 l. Can	12
KIT n° 50	0,50 liter	1 liter Can	12

SEMKITS :

	Total Content	Number per Case
655	55 cc	24
654	100 cc	24

LE JOINT FRANCAIS

SEALANTS ADHESIVES & COATINGS

84/116 rue Salvador Allende, 95870 Bezons - Tél 01.34.23.34.23 - Télécopie 01.34.23.34.99

[http : \www.ljfm.com](http://www.ljfm.com)



APPLICATION PROPERTIES (typical)

- Couleur Base	Red
Accelerator	Black
- Mixing ratio (by weight) Base / Accelerator	10 : 1
- Nonvolatile content (mixed compound)	84 % mini
- Viscosity (Brookfield # 7 @ 2 rpm)	20-65 Pa.s
- Vertical Flow :	
Initial	1 mm
After 20 min	5 mm

- Application Life and Cure Time

Application Life (hours)	Tack Free Time (hours)	To 30 Shore A (hours)
A 2	2	12
		48

PERFORMANCE PROPERTIES (typical)

- Color	Dark red
- Specific Gravity	1,55
- Hardness, Shore A	50
- Low temperature flexibility	- 55° C

Adhesion - Peel strength (N/mm)

	Standard	7days in B Fluids at 60°C
Alclad 2024	0,2	0,1
Stainless Steel	0,1	0,1
Titanium	0,1	0,1
PU 66 abraded	0,3	0,3

Tensile Strength and Elongation :

	Tensile Strength (MPa)	Elongation (%)
- Initial	1,5	240

- Corosion résistance

No sign of corrosion and sealant deterioration after :	
Salt spay methode	5000 hrs
Galvanic cell method	2 weeks
Al/Stainless steel couple	
Al/Titanium couple	
Al/Cadmium plated steel couple	

- Resistance to Salt and Hydrocarbon

No sign of blistering and softening.
No evidence of corrosion

- Resistance to other Fluids :

Excellent resistance to water, alcohols, petroleum-base, synthetic lubricating oils and petroleum-base hydraulique fluids.

NOTE : The above application and performance property values are typical for the material, but are not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

SURFACE PREPARATION

Part shall be cleaned with solvents to remove dirt, grease, and processing lubricants used in manufacturing.

Wash one small aera at a time, then dry with a clean cloth before solvent evaporates to prevent redeposition of oil, wax or other surface contaminants. To maintain a clean solvant supply, always pour the solvent on the washing cloth.

MIXING INSTRUCTIONS

Proper mixing and correct proportions are extremely important if optimum results are to be obtained. Mixing by experienced personnel at a central location is recommended.

CAUTION: Do not mix accelerator with compound until ready to use.

1° Thoroughly stir accelerator in its container until an even consistency is obtained.

2° Thoroughly stir base compound in its container until an even consistency is obtained.

3° Slowly stir the accelerator into the base compound and thoroughly mix approximately 7 to 10 minutes. Be sure to scrape the sides and bottom of the container in order to include all the compound in the mixture and to assure uniform blending. Scrape mixing paddle periodically to remove unmixed compound. Slow mixing by hand is recommended.

Fractional Use of Unit :

When it is desired to use only part of the kit, after homogenization, remove the required quantity.

(§ Application Properties).

Semkit Two-Part Sealant Cartridges:

1° Wear safety glasses.

2° Hold cartridge and pull back dasher rod one fourth.

3° Pull back the dasher rod as injecting as proportionnaly as possible the contents accelerator into the base.

4° Mix material, rotate dasher rod 90° in aspiral clockwise motion; with each stroke turn the dasher rod 90°.

5° When two-parts are mixed thoroughly, pull dasher rod back to the neck of cartridge, grasp cartridge firmly at neck, unscrew dasher rod counterclockwise and remove.

6° Screw nozzle into cartridge, material is ready for extrusion.

For all informations, consult the
Engineering Services of
LE JOINT FRANCAIS.

APPLICATION INSTRUCTIONS

Application life is the period of time that the mixed compound remains at a consistency suitable for application with injection or extrusion guns. Application life is always based on standard conditions at 23° C and 50 % relative humidity. For evry 5° C rise in temperature, application life is reduced approximatetly by half, and for evry 5° C it is approximatly doubled. High humidity at the time of mixing shortens application life.

Apply the sealant with an extrusion gun equipped with 3 to 6 mm tip. Hold gun nearly perpendicular so that extruded sealant will be forced into the lip of seam.

On most application, the fillet should be 3 to 5 mm thick, but heavier fillets can be applied in a single operation, if necessary.

CURING

The lenght of the cure depends on the ambient temperature and relative humidity.

The temperature/time relation ship is approximately the same for curing as it is for application life .

Low humidities may extend the cure several times. Cure may hastened by applying heat up to 55° C.

CLEANING EQUIPEMENT

Equipment should be cleaned immediately after use with methylethylketone. Cured sealant on accessible portions of equipement will peeled off by hand.

STORAGE LIFE

The storage life of **PR 1773 A** is 6 months when stored in the original, unopened containers at temperature below 25°C.

HEALTH PRECAUTIONS

PR 1773 A is a safe material to handle when reasonable care is observed. Ordinary hygienic principles, such as washing the compound from hands before eating or smoking, should be observed. Avoid prolonged contact with skin, contact with open breaks in the skin, and ingestion. In case of contact with skin, wipe off excess then wash with soap and water. Obtain medical attention in case of extreme exposure or ingestion.

For additional health and safety information consult a
Material Safety Data Sheet
which is available upon request

GUARANTEED

We guarantee all our products against faulty materials or preparation. Our sole responsibility shall be to replace, free of charge, those products which prove to be defective, the user being entitled to no indemnity for any reason whatsoever. All recommendations contained herein as to the choice of materials or of certain methods of operation are of an informative character and are based on tests and experiments we believe to be reliable and correct, but accuracy and completeness of such tests are not guaranteed and are not to be construed as a warranty, either express, or implied.

Neither our company, nor any of its collaborators shall be liable to the user for any injury, loss or damage directly or indirectly resulting from the use of, or inability to use, the products, which does not comply with the application instructions as specified in our information manual.

Recommendations or statements other than those contained in a written document signed by an officer of our company shall not be binding upon the company.

XP / 01 / 2001

